

FloroMark Striping & Marking Kits

Product Description: FloroMark is unique among floor marking and striping materials. Tough, glossy and color-rich, it provides excellent hiding in one coat with minimal bleed under tape. Applied at an average of 80 sq/ft per gallon, this hard-working epoxy far outlives its competition, minimizing the need for frequent recoating.

FloroMark is low odor and ultra low VOC. Kits are available in Safety Yellow. A variety of Florock Colorants may be substituted for the yellow color to tint the Neutral base.

Packaging: FloroMark is available in Multi-paks, each containing four-106 ounce kits, in Safety Yellow. For other colors or packaging, please consult your Florock Representative.

Storage: All containers should be stored at 40° F to 95° F and be kept tightly sealed and out of direct sunlight.

<u>Liquid Physical Properties</u>				
Property	Test Method	Pt A	Pt B	Pt C
		<u>X-9424-21A</u>	<u>U0-144</u>	<u>K2-020</u>
Viscosity	ASTM D2198	68,000 cps	33 cps	800 cps
FlashPoint	ASTM D3278	>200° F	>200° F	>100° F
Wt. per gal	ASTM D1475	12.3 lbs	7.9 lbs	12.1 lbs
N.V.W	ASTM D2369	100%	100%	69%
<u>Blended Components</u>				
Blending Ratio	80:18:8 by volume			
Pot Life, 106 oz. Volume*	30 minutes			
Min. Recommended Spread Rate	100 sf/gal			
N.V.W	97%			
Cure time @ 70° F**				
Set to Touch	1 ½ - 2 hours			
Foot Traffic	6 – 8 hrs			
Forklift Traffic	Overnight			
Floor and Air Temp. Limitations***	55°-90° F			
Resin Only, Blended Viscosity	3,500 cps			
Rec. Clean –Up Solvent	S-41 Florobase			
VOC	35 gpl			

*Pot life varies depending upon mass and storage temperature of materials.

** Cooler temperatures require longer dry time. Film thickness effects dry time

***Consult your Florock Sales Representative for Temperatures outside these limits.

Note: FloroGel should not be applied when floor temperature is above 90° F or below 55° F, or when within 5° F of the dew point.

Instructions for Use on Bare Concrete:

1. Prepare surfaces in accordance with instructions in the “Preparation of Concrete Manual”.

2. Apply good quality masking tape to floor where desired. Pour FloroMark Resin Part B into partially filled gallon can of Part A. Mix thoroughly for 3-5 minutes, using a low speed mechanical mixer. Mix Florock Colorant thoroughly in its own container before adding to Neutral resin blend. Blend resin and colorant for 3 more minutes, using a low speed mechanical mixer.

3. Pour FloroMark mixture out in a "ribbon" inside masked-off lines. Spread with long-napped 4" roller, after wetting out roller well. Apply at 10 – 20 mil WFT thickness. Product has 60 minute pot life. Pull tape before epoxy cures.

Note: A second application may be necessary to achieve full hiding. Repeat steps 2 and 3 for a second application.

4. Open floor to light foot traffic after 6-8 hours. Full chemical cure and mar resistance will be achieved in 7 - 10 days.

Chemical Resistance	
Reagent	Spot Test Results
Sulfuric Acid 10%	1
Sulfuric Acid 25%	1
Nitric Acid 10%	1
Hydrochloric Acid 10%	1
Phosphoric Acid 50%	4
Citric Acid 10%	1
Lactic Acid 10%	1
Acetic Acid 10%	1
Sugar Solution 10%	1
Isopropyl Alcohol	5
Acetone	5
Ammonia	1
Brake Fluid	4
Sodium Chloride 20%	1
MEK	5
JP 4 Jet Fuel	2
1 1 1 Trichloroethone	1
Toluene	5
Xylene	5
Methylene Chloride	5
Mineral Spirits	1
MIBK	5
Skydrol	5
Tincture of Iodine	1,S
Water	1

Based on 1 day spot testing. Coating cured 2 weeks prior to testing. Spot Test IAW ASTM D1308, Pencil Hardness Test IAW ASTM D3363

Rating Scale:

- 1 - Excellent. No change in pencil hardness
- 2 - Very Good. 1 unit change in pencil hardness
- 3 - Good. 2 units change in pencil hardness
- 4 - Fair. 3 units change in pencil hardness
- 5 - Poor. 4 or more units change in pencil hardness
- S - Stains

FloroMark Striping & Marking Kits

Instructions for Use over Existing Coatings:

1. If Florock Flooring System is less than 24 hours old, and floor is smooth, proceed with steps 2 - 4 above. When installing FloroMark over an older system, examine existing coating to ensure it is properly prepared and well-bonded to the concrete. Any loose coating should be completely removed and edges should be sanded to a feathered edge.
2. Clean the floor by removing all dirt, oils, grease and other contaminants from the surface, using detergent cleaner.
3. Allow the floor to dry completely. Then sand the existing coating areas to be marked until a powdery residue is evident and all gloss is removed. Sweep or vacuum clean and wipe with solvent to ensure good adhesion of the new system. Prepare any bare concrete by acid etching or mechanical means and prime bare spots with an appropriate Florock Primer.
4. Follow Steps 2-4 of "Instructions For Use On Bare Concrete" above.

Note: To ensure compatibility and adhesion of FloroMark with the existing coatings other than Florock brand, installation of a test patch should be approved prior to striping, and used as the job standard.

Maintenance: Sweep away dust and debris with a broom. Clean on a regular basis with a surfactant type mild detergent. Florock floors never need to be waxed.

Please read material safety data before using product.

DISCLAIMER:

All preceding statements and recommendations are based on experience we believe to be reliable. The use or the application of these products being beyond the control of the Seller or Manufacturer neither Seller nor Manufacturer make any warranty, expressed or implied, as to results or hazard from its use. The suitability, risk and liability whatsoever of a product for an intended use.