

# Florock Seamless Flooring Systems

---

## Architectural Specification – FloroQuartz TL

### Trowel Grade Epoxy Mortar Quartz Flooring System

#### Part 1: General

##### 1.01 System Description

- A. Roller-applied 100% solids, penetrating epoxy primer followed by a troweled quartz mortar, consisting of 100% solids epoxy and graded quartz aggregates, sealed with a 100% solids epoxy grout coat, to achieve a total nominal floor thickness of ¼". Optional urethane topcoats may be applied for additional chemical and abrasion resistance.
- B. This system shall be applied to the prepared substrate(s) as defined by the plans strictly in accordance with the manufacturer's recommendations.

##### 1.02 Submittals

- A. Product Data
  - 1. Current edition of manufacturer's product literature including physical data, chemical resistance, surface preparation, and application instructions.
- B. Samples
  - 1. A hard sample of the proposed system shall be submitted to represent the finished floor.
- C. Warranty
  - 1. Manufacturer's standard warranty
  - 2. Applicator's standard warranty

##### 1.03 Quality Assurance

- A. Qualifications
  - 1. The manufacturer shall have a minimum of ten (10) years' experience in the production, sales, and technical support of polymer-based floor coatings.
  - 2. The applicator shall have a minimum of three (3) years' documented experience in the application of polymer floor coatings to concrete floors and be approved by Florock.
  - 3. Proposed suppliers products shall provide certification that they have ten (10) years' experience in the production of polymer floor coatings and be required to meet all provisions of this specification as well as provide evidence for compatibility between components to the satisfaction of the Architect.
- B. Pre-Bid Conference
  - 1. A pre-bid conference should be held between prospective applicators and the Architect to review surface preparation, application, clean-up procedures, and design issues.

# Florock Seamless Flooring Systems

---

## C. Packing and Shipping

1. All materials are to be delivered to the job site in the manufacturer's original packaging. The product code and other identification marks should be clearly marked and visible.

## D. Storage and Protection

1. All material is to be stored in a cool, dry place out of the direct sunlight and away from any ignition sources. The applicator should refer to the manufacturer's literature and Material Safety Data Sheets for more information.
2. Material Safety Data Sheets are to be kept on site and made readily available for all personnel.
3. Keep containers sealed and ready for use.

## 1.04 Project Conditions

### A. Environmental Requirements

1. Optimum air and substrate temperature for product application is between 55° F (13° C) and 95° F (35° C). For temperatures outside of this range, consult the manufacturer for product application suggestions.
2. Verify the work environment is properly equipped with vapor barriers and perimeter drains.
3. Maintain proper lighting throughout the work environment; the lighting should be comparable to the final lighting level of the space.
4. Store and dispose of any waste in accordance with regulations of local authorities.

### B. Safety Requirements

1. "No Smoking" signs shall be posted throughout the work area prior to application.
2. The owner shall be responsible for removing any foodstuffs from the work area.
3. Open flames, spark producing tools/items, and ignition sources shall be removed from the work area prior to application.
4. Only work-related personnel shall be allowed within the work area.

## 1.05 Warranty

### A. Coordination

1. The manufacturer offers a full, one-year warranty against defects in materials. Warranties concerning the installation of the material are solely the responsibility of the applicator.

# Florock Seamless Flooring Systems

---

## Part 2: Products

### 2.01 Manufacturer

- A. Florock Polymer Flooring  
1120 W. Exchange Avenue  
Chicago, IL 60609  
Phone: (773) 376-7132; (800) 356-7625  
Fax: (773) 376-0945  
<http://www.florock.net>

### 2.02 Materials

- A. Primer
  - 1. The primer shall be a 100% reactive, epoxy-based, penetrating primer that exhibits chemical resistance: Floropoxy 47-series epoxy.
- B. Mortar (Matrix Coat)
  - 1. The mortar shall consist of a three-component mixture of 100% solids epoxy, activator, and graded aggregates: FloroBuild System 4805 or 4900 Trowel Quartz Epoxy
- C. Grout Coat
  - 1. Grout with a 100% solids, chemical resistant epoxy: Floropoxy 4805, 4860 or 4865
- D. Optional Topcoat
  - 1. Apply 1-2 topcoats of a Florock high performance, color-stable, chemical resistant urethane, exhibiting excellent chemical and abrasion resistant properties.

### 2.03 Properties

- A. The coating system should meet the following physical properties:

#### Cured System Properties

<u>Chemical Properties</u>	<u>FloroQuartz TL</u>
Compressive Strength, ASTM C579	10,500 psi
Tensile Strength, ASTM C370	2,100 psi
Flexural Strength, ASTM C580	4,300 psi
Flexural Modulus of Elasticity, ASTM C580	2.0 x 10E6 psi
Indentation, MIL-D-3134F	No Indentation
Hardness, Shore A/D, ASTM D2240	90

# Florock Seamless Flooring Systems

Impact Resistance, ASTM D2240	>160 in/lbs.
Bond Strength, ACI Committee #503, pg. 1139-1141	>400 psi
Abrasion Resistance, Taber Abrader CS-17 Wheel, 1000 gm load, 1000 cycles, ASTM D4060	0.04 gm loss
Heat Resistance Limitation, Continuous Exposure	140°F / 60°C
Coefficient of Friction, ASTM D2047	0.6
Flammability, ASTM D635	Self-Extinguishing
Thermal Coefficient of Linear Expansion, ASTM C531	1.8 x 10-5 in/in/°C

## Part 3: Execution

### 3.01 Inspection

#### A. General

1. Examine the areas and conditions where FloroChip is to be installed and notify the Architect of any conditions detrimental to the proper and timely completion of the work. Do not proceed with the work until unsatisfactory conditions have been corrected by the contractor in a manner acceptable to the Architect.

### 3.02 Preparation

#### A. General

1. Consult the manufacturer's recommendations for concrete substrate preparation before proceeding.

#### B. Patching and Joint Preparation

1. Before application, the floor shall be examined for spalls, pits, holes, cracks, non-functional joints, etc. These must be treated after preparation and before application with the suitable Florock products. For functional or expansion joints, these shall be treated with 100% solids elastomeric resin having a minimum elongation of 150%, Florock System 6500.

#### C. Concrete Surfaces

1. Shot-blast, diamond grind or power scarify as required to obtain clean, open, porous concrete. Remove sufficient material to provide a sound surface, free of laitance, glaze, efflorescence, and any bond-inhibiting curing compounds or form release agents. Remove grease, oil, and other penetrating contaminants. Repair damaged and deteriorated concrete to acceptable condition; leave surface free of dust, dirt, laitance, and efflorescence.

# Florock Seamless Flooring Systems

---

## D. Materials

1. Mix components when required, and prepare materials according to flooring system manufacturer's instructions.

## 3.03 Application

### A. General

1. The system shall be installed in the order described below:
  - a. Substrate Preparation
  - b. Priming
  - c. Mortar (Matrix Coat) Application
  - d. Grout Coat & Optional Topcoat(s) Application
2. Concrete surfaces on grade shall have been constructed with a vapor barrier to help protect against the effects of vapor transmission and possible delamination of the system. Refer to manufacturer's concrete preparation instructions for additional recommendations.
3. The surface should be dry prior to application of any of the aforementioned steps. Furthermore, the substrate shall always be kept clean, dry, and free of any contaminants.
4. The handling and mixture of any material associated with the installation of the system shall be in accordance with the manufacturer's recommendations and approved by the Architect.
5. The system shall follow the contours of the substrate unless otherwise specified by the Architect.
6. A neat finish with well-defined boundaries and straight edges shall be provided by the applicator.

### B. Priming

1. All areas considered for the application shall be primed with the manufacturer's primer to seal and penetrate the substrate in preparation for applying the basecoat (matrix coat) and grout coat.
2. Porous concrete substrates may require additional applications of primer.

### C. Mortar

1. The mortar coat shall consist of the manufacturer's approved resin and graded quartz aggregates to resurface the floor, seal the surface and give the floor impact and chemical resistance.

### D. Grout Coat and Optional Topcoat(s)

1. The grout coat and optional topcoat(s) shall be consistent with the manufacturer's recommendations for the system.

## Florock Seamless Flooring Systems

---

2. No traffic or equipment shall be permitted on the floor during the curing period.

### 3.04 Field Quality Control

#### A. Tests & Inspection

1. The following tests shall be performed by the applicator and recorded during application to submit to the Architect:

##### a. Temperature during installation

1. Air
2. Substrate
3. Dew Point

### 3.05 Cleaning

#### A. Disposal

1. Properly remove and dispose of any excess materials.

-- End --