

FloroSurface Primer Self-Leveling Latex-Based Primer

Product Description: FloroSurface Primer is a re-emulsifiable, latex-based primer, compatible with the latex in FloroSurface Underlay cementitious self-leveling underlayment.

Product Advantages:

- Self-leveling applications
- Porous Substrates
- ZERO VOC

Packaging: FloroSurface Primer

- 5 Gallon pail (18.93 L) with pour spout

Storage: All containers should be stored at 45° F to 85° F (7° C to 29° C) and be kept tightly sealed and out of direct sunlight. The shelf life for this product is 12 months from date of manufacture.

Coverages: FloroSurface Primer coverage rate varies depending upon surface porosity. A typical rate of 250-300 SF/gallon (6.1-7.3 m²/L) can be expected.

Substrate Preparation: Properly prepare subfloor to receive FloroSurface Primer, according to instructions of individual FloroSurface product. All supporting surfaces shall be structurally sound, solid and stable. They shall be free of dust, oil, grease, paint, tar or other contaminants that may act as a bond breaker. Application over textured surfaces provides the best bond. Concrete that has been steel troweled should be mechanically prepared using shot-blaster, diamond grinder, or other approved method. A minimum of CSP 3 (Concrete Surface Profile, Level 3) is recommended.

Application: SHAKE or STIR before application. Using a long handle roller, soft bristle broom or brush, apply FloroSurface Primer at full strength at a rate of 250-300 SF/gallon (6.1-7.3 m²/L). Do NOT dilute. Ensure a complete and uniform coverage. Allow to become very tacky or dry—approx. 1 hour. DO NOT apply in excessive amounts; avoid puddling or pooling. FloroSurface Primer must be completely dry and tacky before covering.

Freeze/Thaw Stable: If frozen, allow to thaw at room temperature at 70° F (21° C), then stir. If smooth, primer should be safe to use.

Please read material safety data before using product.

Disclaimer: All statements and recommendations are based on experience we believe to be reliable. The use or the application of these products being beyond the control of the Seller or Manufacturer, neither Seller nor Manufacturer make any warranty, expressed or implied, as to results or hazard from its use. The suitability, risk and liability of a product for an intended use shall be solely up to the User.